

Realistic

PROPERTIES	STANDARD	UNIT	TEST RESULT
Plank size	EN 427	cm	121,92 x 22,86 cm
Thickness	EN 428	mm	2,00 mm
Wearlayer	EN 429	mm	0,30 mm
Surface treatment			BP embossing + PUR
Bevel			No
Weight per sqm	EN 430	gr/m2	3630
Pieces per box		piece	12
Sqm per box		m2	3,34
Boxes per pallet		box	56
Sqm per pallet		m2	187,29
Classification	EN 685	class	23-31
Fire classification	EN 13501-1	class	Bf1-S1
Slipresistance	DIN 51130	class	R9
	EN 13893	class	DS
Weargroup	EN 660-1		T
Residual indentation	EN 433		0.05 mm
Thermal conductivity	EN 12667:2001		0.076 W/(m·K)
Thermal resistance	EN 12667:2001		0.036 m²·K/W
Electrostatic properties	EN 1815		<2.0 KV
Castor chair	EN 425		yes type W EN12529
Dimensional stability	EN 434		≤0.12%
Light fastness	ISO 105-BO2	degree	level ≥6 method A
Determination of impact sound	E 492-09		IIC=63
Sound reduction	ISO 717-2		4 dB
Chemical resistance	EN 423		yes
Floor heating system		degree	suitable max.27°C
CE marking	EN 14041		EN 14041:2004+AC:2005+AC:2006
Guarantee			residential 10 years - commercial 5 years